

TECANYL 731

Chemical Designation :

DIN-Abbreviation:

Colours, fillers:

Polyphenylenether

PPE

grey

Main features

| strong
 | very good electrical insulation
 | hot water resistant

| tough
 | easily welded and bonded
 | sensitive to stress cracking

Preferred Fields

| mechanical engineering
 | transport and conveyor technology
 | precision engineering
 | food technology

| automotive engineering
 | electrical engineering
 | domestic appliance
 | medical technology

Applications

Pump parts, switch parts, pump impeller, plugs, ccontact rail, insulators, housing parts, household articles, rollers, automotive parts

Properties

Mechanical

Tensile strength at yield

Elongation at yield

Tensile strength at break

Elongation at break

dry / moist

55

5

MPa

%

MPa

%

standard

DIN EN ISO 527

DIN EN ISO 527

Modulus of elasticity in tension	2300	MPa	DIN EN ISO 527
Modulus of elasticity after flexural test		MPa	
Hardness	125		DIN 53 456 (Kugeldruckhärte)
Impact strength 23° C (Charpy)	n.b.	KJ/m ²	DIN EN ISO 179 (Charpy)
Creep rupture strength after 1000 h with static load		MPa	
Time yield limit for 1% elongation after 1000 h	21	MPa	
Co-efficient of friction p = 0,05 N/mm ² v=0,6 m/s on steel, hardened and ground	0,4		
Wear p = 0,05 N/mm ² v=0,6 m/s on steel, hardened and ground	90	µm/km	

Thermal

	dry / moist		standard
Crystalline melting point		°C	
Glass transition temperature	150	°C	DIN 53 765
Heat distortion temperature HDT, Method A	130	°C	ISO-R 75 Verfahren A (DIN 53 461)
Heat distortion temperature HDT, Method B	138	°C	ISO-R 75 Verfahren B (DIN 53 461)
Max. service temperature			
short term	110	°C	
long term	85	°C	
Thermal conductivity (23° C)	0,22	W/(K·m)	
Specific heat (23° C)	1,2	J/g.K	
Coefficient of thermal expansion (23–55°C)	7	10 ⁻⁵ /K	DIN 53 752

Properties

Electrical	dry / moist		standard
Dielectric constant (10^6 Hz)	2,6		DIN 53 483, IEC-250
Dielectric loss factor (10^6 Hz)	0,001		DIN 53 483, IEC-250
Specific volume resistance	10^{13}	$\Omega \cdot \text{cm}$	DIN IEC 60093
Surface resistance	10^{15}	Ω	DIN IEC 60093
Dielectric strength	50	kV/mm	DIN 53 481, IEC-243, VDE 0303 Teil 2
Resistance to tracking	KA 1		DIN 53 480, VDE 0303 Teil 1

Miscellaneous	dry / moist		standard
Density	1,06	g/cm^3	DIN 53 479
Moisture absorption (23°C/50RH)	0,1	%	DIN EN ISO 62
Water absorption to equilibrium	0,2	%	DIN EN ISO 62
Flammability acc. to UL standard 94	HB		

(1) Testing of semi-finished products

The above information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of chemical resistance, of certain properties and the suitability of our products and their applications. Our products are not destined for use in medical and dental implants. Existing commercial patents must be observed. Unless otherwise stated, these values represent averages taken from injection moulding samples, dry as moulded. We reserve the right to make technical alterations.
