

## KASI®-AS Hart PC Antistatic coating for PC

Abrasion resistant coating for polycarbonate providing effective protection against electrostatic charging and preventing attraction of dust and dirt.

### Typical properties

Revision: 09/04	Standard	Dimension	KASI®-AS DUR
<b>General properties</b>			
Bulk density*	ISO 1183	g/cm <sup>3</sup>	1,2
Surface resistance	ASTM D257	Ω	10 <sup>4</sup> -10 <sup>8</sup>
<b>Mechanical characteristics</b>			
Tensile strength*	ISO 527	MPa	60
Elongation at tear*	ISO 527	%	110
Modulus of elasticity*	ISO 527	MPa	2200
Impact resistance*	ISO 179	kJ/m <sup>2</sup>	not broken
Pencil hardness			6H
<b>Thermal characteristics</b>			
Vicat diluting temperature VST/B 50*	ISO 306	°C	150
Constancy temperature* HDT/A (1,8 N/mm <sup>2</sup> )	ISO 75	°C	135
Temperature of permanent use*	DIN 53446	°C	115
Linear coefficient of cubical thermal expansion (α) 0 – 50 °C	DIN 53752	K <sup>-1</sup>	60 x 10 <sup>-6</sup>
Heat conductivity (λ)*	DIN 52612	W/mK	0,21
Specific heat (c)*		J/gK	1,3
<b>Optical characteristics</b>			
Colour			slightly grey
Transparency 380-780 nm D = 3 mm	DIN 5036	%	≤70
<b>Special characteristics</b>			
Behaviour in fire*	DIN 4102	Fire classification	B 2

\*The information applies to the carrier material.

The information is based on presently available knowledge and experiences. They do not release the processor from own tests and trials. A legally binding assurance of certain characteristics or the suitability for a specific purpose of use cannot be derived from it. Possible patent rights as well as existing laws or provisions must be taken into account by the receiver of our products, who bears the responsibility.